

Plymouth Rubber Europa S.A

# L969 Plyvolt

Linerless EPR High Voltage Insulating and Jacketing Tape

## Description

L969 Plyvolt is an ethylene propylene rubber based, high voltage tape possessing excellent electrical, chemical and physical properties. L969 is a linerless, self-bonding tape that permits much quicker taping speeds than a tape with a liner and yields a uniform, void-free build-up. The excellent stretch of L969 Plyvolt allows conformability to the most complex shapes and contours. L969 Plyvolt is compatible with all extruded cable insulations and is specially formulated to have excellent thermal conductivity that will allow the heat to dissipate from a joint. It is flame retardant and meets typical industry standards.

#### Recommended Uses

For insulating and jacketing of splices on power cable from 600 volts through 69,000 volts and for building stress cones and jacketing of terminations on power cable from 600 volts through 35,000 volts. Insulate and protect bus bars and joints.

## **Specifications**

Property	Value	Unit	<b>Test Method</b>
Physical			
Color	Black		= = =:
Thickness	0,76	mm	ASTM D 4388
	0.030	inch	<b>ASTM D 4388</b>
Tensile Strength	400	psi	<b>ASTM D 4388</b>
	2,8	MPa	<b>ASTM D 4388</b>
Elongation	1140	%	<b>ASTM D 4388</b>
Fusion	5/64 Max.	inch	<b>ASTM D 4388</b>
	2 Max.	mm	<b>ASTM D 4388</b>
Heat Resistance	130	°C	<b>ASTM D 4388</b>
Operating Temperature			
Continuous	90	°C	<b>ASTM D 4388</b>
Emergency Overload	130	°C	<b>ASTM D 4388</b>

Chemical			
Water Absorption	0,06	%	ASTM D 570
Ozone Resistance	Pass	Visual	<b>ASTM D 4388</b>
UV Resistance	Pass	Visual	<b>ASTM D 4388</b>

Electrical			
Dielectric Strength	39,4	kV/mm	ASTM D 4388
	1000	V/mil	<b>ASTM D 4388</b>
Dissipation Factor			
After water immersion	0,005		<b>ASTM D 4388</b>
After hot water immersion	0,015		<b>ASTM D 4388</b>
Permitivity			
After water immersion	2,9		<b>ASTM D 4388</b>
After hot water immersion	3,1	7.7.7	<b>ASTM D 4388</b>
Volume Resistivity			
96 h @ 23 °C and 50 % RH	10 <sup>16</sup>	Ohmxcm	<b>ASTM D 4388</b>
96 h @ 23 °C and 96 % RH	10 <sup>13</sup>	ohmxcm	ASTM D 4388

#### **Features**

- Linerless
- Self-bonding
- Outstanding corona and ozone resistance
- High thermal conductivity
- Flame retardant
- UV resistant
- Excellent moisture, corrosion and chemical resistance
- Lead-free

### **Standard Sizes**

- 3/4 in x 30 ft
  19 mm x 9 m
- 1 in x 30 ft 25 mm x 9 m
- 1 1/2 in x 30 ft 38 mm x 9 m
- 2 in x 30 ft 51 mm x 9 m

Consult factory for other sizes



Data in table represent average test results and are not to be used for specification purposes. The product user should make his/her own tests to determine the product's suitability for the intended use.

LIMITED WARRANTY: Plymouth warrants that its Product will substantially conform to that products written specifications exclusively contained in its Plymouth product data sheet for a period of one (1) year from the date of shipment, (Unless provided otherwise in product's data sheet). Plymouth makes no warranty to the distributor, its customers, or the product's end user for the products merchantability and/or suitability for his/its intended use or purpose, and buyer shall assume all risks associated therewith. Provided that the product is proved to be defective within the terms described above, and provided buyer shall have first compiled with all return policies of Plymouth, PLYMOUTHS SOLE OBLIGATION AND BUYERS EXCLUSIVE REMEDY UNDER THIS PRODUCT WARRANTY SHALL BE TO REPLACE SUCH QUANTITY OF THE PRODUCT AS IS PROVED TO BE DEFECTIVE WITHIN THE TIME PERIOD SPECIFIED ABOVE. EXCEPT AS EXPRESSLY SET FORTH HEREIN, PLYMOUTH MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED. In no event shall Plymouth be liable for collateral, consequential, indirect or incidental damages arising out of, or connected in any way with the supply of products, (rev. 195)